TÜV Rheinland Nederland B.V.



Return address: P.O. Box 2220, 6802 CE ARNHEM, The Netherlands

Superior Manufacturing Group-Europe B.V. Att. Mrs. G. Dirckx Achterzeedijk 57 NL-2992 SB BARENDRECHT The Netherlands TÜV Rheinland Nederland B.V. The Netherlands

Postal address: P.O. Box 2220 6802 CE ARNHEM

Parking and delivery: Westervoortsedijk 73 6827 AV ARNHEM

www.tuv.com/nl

T +31 88 888 7888

Jaring.de.Wolff@nl.tuv.com

Report

Project number: 89209491 **Report number:** 89209491.03en Date

29/03/2016

Received:

A protective mat, marked as: **"827 Anti-stat POP"**; TÜV-reference: MT16-91559.03

Project number 89209491

Report number 89209491.03en

Sampling procedure:

The samples are selected by the applicant. The test house has had no influence on the sampling procedure.

Phone number client

+ 31 (0) 180 643 115

Fax number client

The samples have been received on 04/03/2016.

Order:

To determine electrical resistance according to IEC 61340-4-1*

* The test is completely or partially conducted by a subcontractor

Article

827 Anti-stat POP

Results:

See page three up to and including five.

Appendix - none -

Appendix:

None.

TRN applies General Terms & Conditions which are filed at the office of the Clerk for civil affairs at the Court in Zutphen (the Netherlands) under number 35/2010, dated November 17th 2010.



PRODUCT IDENTIFICATION

: Superior Manufacturing Group-Europe B.V.

Name : 827 Anti-stat POP*

Material : 100% vinyl*

Mass (kg/m2) : 3*

Total thickness (mm) : 6.4*

Size (cm x cm) : $63 \times 120^*$

* Applicant's declaration

Applicant

Date 29/03/2016

Project number 89209491

Report number 89209491.03en

Article 827 Anti-stat POP

Page 2/5



Figure 1, Picture of the received sample



TEST RESULTS

Date 29/03/2016

Project number 89209491

Report number 89209491.03en

Article

827 Anti-stat POP

Page 3/5

Electrical resistance of floor coverings and installed floors

Method IEC 61340-4-1:2004

Test period : 11/03/2016 - 21/03/2016

Pre-conditioning conditions : 23±2°C and 12±3% R.H.

Conditioning time : 72 h

Test conditions : 23±2°C and 12±3% R.H.

Support plates used: Yes, wood plate (2000 x 2000 x 20 mm)

Horizontal resistance (point to point)

Sample: MT16-91559.03 (827 Anti-stat POP)

Sample no.	Measurement no.	Voltage (V)	Resistance (Ω)	Average (Ω)
1	1	100	2.50x10 ⁸	2.43x10 ⁸
	2	100	2.80x10 ⁸	
	3	100	2.40x10 ⁸	
	4	100	2.10x10 ⁸	
	5	100	2.50x10 ⁸	
	6	100	2.30x10 ⁸	
2	1	100	2.50x10 ⁸	2.37x10 ⁸
	2	100	2.80x10 ⁸	
	3	100	2.40x10 ⁸	
	4	100	2.00x10 ⁸	
	5	100	2.30x10 ⁸	
	6	100	$2.20 \mathrm{x} 10^8$	
3	1	100	3.30x10 ⁸	2.37x10 ⁸
	2	100	2.40x10 ⁸	
	3	100	2.30x10 ⁸	
	4	100	2.00x10 ⁸	
	5	100	2.10x10 ⁸	
	6	100	2.10x10 ⁸	



Horizontal resistance (point to earth connector)

Sample: MT16-91559.03 (827 Anti-stat POP)

Sample no.	Measurement no.	Voltage (V)	Resistance (Ω)	Average (Ω)
1	1	100	7.20x10 ⁸	5.88x10 ⁸
	2	100	7.40x10 ⁸	
	3	100	5.60x10 ⁸	
	4	100	6.00x10 ⁸	
	5	100	4.00x10 ⁸	
	6	100	5.10x10 ⁸	
2	1	100	7.10×10^{8}	5.73x10 ⁷
	2	100	7.20x10 ⁸	
	3	100	5.60x10 ⁸	
	4	100	5.80x10 ⁸	
	5	100	3.70x10 ⁸	
	6	100	5.00x10 ⁸	
3	1	100	7.60×10^8	6.10x10 ⁷
	2	100	7.80x10 ⁸	
	3	100	6.00x10 ⁸	
	4	100	6.00x10 ⁸	
	5	100	3.80x10 ⁸	
	6	100	5.40x10 ⁸	

Date 29/03/2016

Project number 89209491

Report number 89209491.03en

Article 827 Anti-stat POP

Page 4/5



Vertical resistance

Sample: MT16-91559.03 (827 Anti-stat POP)

Report	numbe
892094	91.03en

89209491

Project number

Article 827 Anti-stat POP

Page 5/5

Date 29/03/2016

Sample no.	Measurement no.	Voltage (V)	Resistance (Ω)	Average (Ω)
1	1	100	7.20x10 ⁶	9.45x10 ⁶
	2	100	9.90x10 ⁶	
	3	100	9.90x10 ⁶	
	4	100	8.70x10 ⁶	
	5	100	$1.00 \mathrm{x} 10^7$	
	6	100	$1.10 \text{x} 10^7$	
2	1	100	1.10x10 ⁷	1.08x10 ⁷
	2	100	9.60x10 ⁶	
	3	100	1.10×10^7	
	4	100	$1.10 \text{x} 10^7$	
	5	100	$1.00 \mathrm{x} 10^7$	
	6	100	1.20x10 ⁷	
3	1	100	$1.10 \text{x} 10^7$	1.02x10 ⁷
	2	100	$1.10 \text{x} 10^7$	
	3	100	9.60x10 ⁶	
	4	100	8.70x10 ⁶	
	5	100	9.30x10 ⁶	
	6	100	$1.10 \text{x} 10^7$	

Author:

Mr. J. de Wolff

Review:

Mr. R. Boerboom

All rights reserved.

No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V. The results are based upon the samples received and have not to be representative for the total production. TÜV Rheinland Nederland B.V. had no influence on the sampling.

In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties.

© 2010 TÜV Rheinland Nederland B.V.

(end of report)