

TEST REPORT

DATE: 12/31/2008	TEST NUMBER: 118727
CLIENT	Superior Manufacturing Group
TEST METHOD CONDUCTED	Surface Flammability of Carpets and Rugs (16 CFR Chapter II, Subchapter D, Part 1630 CPSC FF 1-70) also referenced as ASTM

D2859

DESCRIPTION OF TEST SAMPLE					
IDENTIFICATION	Rubber Brush				
COLOR	Black				
ROLL	345S3660BL				
CONSTRUCTION	Rubber Mat				
FIBER					
BACKING					
REFERENCE					

GENERAL PRINCIPLE

This test method is intended to measure the response of finished textile floor covering materials when exposed to an ignition source under controlled laboratory conditions. It is applicable to all types of textile floor coverings whether constructed from natural or man-made materials.

TEST CRITERION

The uncharred area of the test specimen must be greater than one inch in at least seven of the eight specimens tested in order to meet the acceptance criterion.

TEST RESULTS

	SPECIMEN NUMBER										
	1	2	3	4	5	6	7	8			
Uncharred Area (Inches)	3.6	3.6	3.6	3.6	3.6	3.6	3.6	3.6			

NOTE: This Sample was tested on the face side.

This sample PASSES the Federal Flammability Standard DOC FF 1-70.

Lang atling APPROVED BY:



This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to fhose samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory hc. shall not be used under any circumstance in advertising to the general public.