

C3

Hydroentangled 100% polyester, especially smooth and soft.

Property	Typical Value	Test Method
Basis Weight		
(oz/yd ²)	2.0	
(g/m ²)	68	
Thickness		
(mils)	11	
(mm)	0.279	
Sorptive Capacity		
Intrinsic (mL/g)	4.32	IEST-RP-CC004.3
Extrinsic (mL/m ²)	322	IEST-RP-CC004.3
Extractables (mg/g)		
DI Water, DIW	0.015	IEST-RP-CC004.3
Isopropyl Alcohol, IPA	0.057	IEST-RP-CC004.3
Ions (ppm)		
Sodium	<11	IEST-RP-CC004.3
Chloride	2.1	IEST-RP-CC004.3
Particles (million/m²)		
0.5 - 5.0 µm	3.9	IEST-RP-CC004.3
5.0 - 100 µm	0.1	IEST-RP-CC004.3
Fibers (fibers/m²)		
>100 µm	93,073	IEST-RP-CC004.3

Notes:

- 1) Data shown are typical values and should not be used as product specifications.
- 2) Valid product comparisons may only be obtained through side-by side testing in the same test facility, under similar conditions. Current and/or comparison data may be available.
- 3) The Manufacturer makes general recommendations on which wipers are suitable for different cleanroom classifications. However, specific applications may affect that recommendation. The final decision should be made by the end user for their particular application.