



Fast-drying, water-dilutable, opaque staining satin paint based on acrylate dispersion. Primer and top coat in 1-pot.

- Moisture regulation
- Fast drying
- High elasticity
- Good outdoor durability
- Good gloss retention
- Less environmental polluting

productpage Ralston Aqua 3-in-1 Satin

#### Intended use

Exterior

As an undercoat, intermediate coat and top coat (1-pot system) for exterior use. Especially suitable for (rough) woodwork requiring moisture regulation.

#### Colors

Colours All colours available via the Ralston AQ colour mixing system.

All colours available via the Ralston UNI Plus colour mixing system.

#### **Performance and features**

Binder Acrylate

Pigment High quality pigments

Density at 20°C (kg/dm3), approx. 1.25 Viscosity at 20°C (K.U.), approx. 95 Solids content (volume %), approx. 42

Drying time (20°C / 65% R.H.) Dust-free after approx.1 hr, recoatable after approx. 4 hr.

Drying times are average values and provided as an indication only

actual drying time will depend on weather conditions, film thickness and choice of colour. Darker colours, applied in lower temperatures will take longer to dry than

whites and lighter colours.

Elasticity (mm) 7

Gloss level Satin gloss, approx. 35 G.U. at 60°

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

### **Processing**

Application tool brush

roller



Dilution Ready to use. If necessary max. 5% water.

Tools/equipment cleaning Water.

Application temperature / R.H. Min. 10 - max. 25 ambient and substrate temp., relative humidity max. 85.

Substrate temperature min. 3°C above dew point.

Theoretical coverage (m2/l)

Practical coverage Depending on the application method and the substrate, 60 - 85% of the

theoretical coverage.

Film thickness 35 microns dry film thickness = approx. 83 microns wet film thickness

Mixing Stir thoroughly before use.

Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating,

as well as on the drying and gloss of the applied coating.

**Maintenance** 

Maintenance interval (years) Approx. 6

Depending on location/ situation, surface to be treated, construction system,

applied paint system and colour, mechanical impacting, etc..

The annual cleaning and touching up of damage prolongs the condition of the

substrate and the paintwork.

**Environment and Health** 

Flash point (°C) >110

Safety instructions

The user is subject to the national legislation regarding safety, health and

environment. For more information and current data, see the latest version of the

Safety Data Sheet.

EU limit value VOC EU limit value for this product A/d: 130 g/l 2010. This product contains a maximum

of 130 g/I VOCs.

BREEAM We herewith conform that our product can be used in compliance with BREEAM

International New Construction. As per HEA 9, requirend evidence – completion

phase: C 1.1 through to 1.8

in evidence of compliance, the following must be submitted: 1. VOS Volatile

Organic Substance content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/d: 130 g/l 2010. This product contains a maximum of

130 g/l VOCs. We apply the above harmonization procedure as recommended by

the Dutch Green Building Council.

Belgian emission label The product complies with the limit values and other stipulations of the Royal

Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as

published in the Belgian Government Gazette of 8 August 2014.

French emission label A

Item details

Packaging (I) 1, 2.5

Storage Cool and above freezing point

do not allow product quality to deteriorate during storage.



Use within

12 Months in unopened packaging.

After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and moulds free rein from outside, which could spoil the product.



### System composition - advices

#### New, exterior, untreated, wood

- clean / degrease and sand
- prime with Ralston Agua 3-in-1 Satin
- pre-finish with Ralston Aqua 3-in-1 Satin
- finish with Ralston Agua 3-in-1 Satin

#### Existing, exterior, treated, wood

- remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston Aqua 3-in-1 Satin
- pre-finish patches or entire surface with Ralston Aqua 3in-1 Satin
- finish with Ralston Agua 3-in-1 Satin

#### General remarks on paint systems and preparation

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

#### Regularly clean and repair any damage to paintwork

Regularly (preferably annually), clean the paintwork and repair any physical or other damage to the substrate or paintwork. This will have a beneficial effect on the condition of the painted object and its paint coating.

#### Adhesion between paint layers

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

#### Regularly check the dew point

When working in lower temperatures, check the dew point frequently. Never apply new paint/coating onto a substrate with condensation (dew). If you do so, the adhesion and film formation will be degraded. Moisture also causes poor drying, and can ruin the gloss.

#### Repairs and compatibility with paint

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

### Pretreatment, wooden substrates

Remove dirt and any weathered and/or degraded parts from wood and wood-based panels prior to application of the paint system in order to obtain a clean and sound substrate. By rounding off sharp edges, a longer protection of the substrate is obtained. Wood may contain up to 18% moisture during treatment.

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Ralston Colour & Coatings B.V. expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross negligence.



Ralston Colour & Coatings B.V.
Part of Royal Van Wijhe Verf
Russenweg 14
P.O. Box 205
8000 AE Zwolle
Netherlands

T:+31(0)38 - 429 11 00 F:+31(0)38 - 421 04 14

www.ralstoncolour.com info@ralstoncolour.com

CoC 05063230