



- Ralston Industrial Satin
- Ralston Industrial High-Gloss
- Ralston UniCoat 3-in-1

• paint • passion • people

**Ralston**  
COLOUR & COATINGS



### Ralston Industrial Satin

**Intended Use**  
As pre- and finishing coat on pre-treated metal.



Exterior  
Interior



### Ralston Industrial High-Gloss

**Intended Use**  
As pre- and finishing coat on pre-treated metal.



Exterior  
Interior



### Ralston UniCoat 3-in-1

**Intended Use**  
As universal primer and finishing coat on (un)treated metal and plastic surfaces.



Exterior

	Ralston Industrial Satin	Ralston Industrial High-Gloss
Theoretical Coverage *	13,2 m <sup>2</sup> /l	12,9 m <sup>2</sup> /l
Drying Time Condition	20 °C / 65 % R.H.	20 °C / 65 % R.H.
Dust-Free Drying Time **	2,5	2,5
Tack-Free Time **	3,5	3,5
Time To Recoat **	16	16
Wet Film Thickness	76 Mμ	78 Mμ
Dry Film Thickness	35 Mμ	35 Mμ
Gloss Level	Satin gloss, approx. 35 G.U. at 60 °	High gloss, approx. 80 G.U. at 60 °

	Ralston UniCoat 3-in-1
Theoretical Coverage *	11,4 m <sup>2</sup> /l
Drying Time Condition	20 °C / 65 % R.H.
Dust-Free Drying Time **	0,25
Time To Recoat **	3,5
Gloss Level	Satin gloss, approx. 30 G.U. at 60 °

Part of  
Royal Van Wijhe Verf

**Ralston**  
COLOUR & COATINGS

Ralston Colour & Coatings B.V.  
Postbus 205, 8000 AE Zwolle  
Nederland

+31(0)38 - 429 11 00  
info@ralstoncolour.com  
www.ralstoncolour.com

2020-01