

# Product Data Sheet

## Ralston Aqua All-Primer BIOseries



High quality, filling, universal, water-soluble adhesive primer based on acrylate technology with a high biobased content.

- Excellent adhesion
- Universal recoatable
- 20-40% Biobased
- Excellent body
- Recoatable in 4 hours
- Extended wet edge time
- Excellent flow
- Good coverage
- Easy application
- Low solvent

[productpage Ralston Aqua All-Primer BIOseries](#)

### Intended use

Exterior  
Interior  
Exterior and interior, as a primary and precoat resp. an adherent primer for wood, aluminium, stony surfaces, synthetics (hard pvc) and sendzimir galvanized steel. Can be applied over the existing traditional paintwork after first thoroughly cleaning and sanding the surface. As a primary coat for the Ralston Aqua and Red label paints.

### Colors

Colours All colours available via the Ralston AQ colour mixing system.  
All colours available via the Ralston UNI Plus colour mixing system.

### Performance and features

Binder	Acrylate technology
Pigment	High quality pigments and specific fillers
Density at 20°C (kg/dm <sup>3</sup> ), approx.	1.3
Viscosity at 20°C (K.U.) , approx.	114
Solids content (volume %) , approx.	40
Drying time (20°C / 65% R.H.)	Dust-free after approx.0.5 hr, recoatable after approx. 4 hr. The stated drying times are typical and depend on such factors as temperature and humidity.
Elasticity (mm)	6
Gloss level	Matt, approx. 10 G.U. at 60°

NOTE: The properties and specifications can vary depending on the colour. The values stated are typical.

### Processing

Application tool	brush roller air spray
------------------	------------------------------

# Product Data Sheet

## Ralston Aqua All-Primer BIOseries

Dilution	Ready to use. If necessary max. 5% water.
Tools/equipment cleaning	Water.
Application temperature / R.H.	Min. 7 - max. 25 ambient and substrate temp., relative humidity max. 85. Substrate temperature min. 3°C above dew point.
Theoretical coverage (m <sup>2</sup> /l)	11.4
Practical coverage	Depending on the application method and the substrate, 60 - 85% of the theoretical coverage.
Film thickness	35 microns dry film thickness = approx. 88 microns wet film thickness
Mixing	Stir thoroughly before use. Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the applied coating.

### Environment and Health

Flash point (°C)	>100
Safety instructions	The user is subject to the national legislation regarding safety, health and environment. For more information and current data, see the latest version of the Safety Data Sheet.
EU limit value VOC	EU limit value for this product A/d: 130 g/l 2010. This product contains a maximum of 130 g/l VOCs.
BREEAM	We herewith conform that our product can be used in compliance with BREEAM International New Construction. As per HEA 9, requirend evidence – completion phase: C 1.1 through to 1.8 in evidence of compliance, the following must be submitted: 1. VOS Volatile Organic Substance content as determined by product recipe. 2. Products grouped by category in accordance with European Decopaint Directive 2004/42/EC – Enclosure 2: Emission norm for paints, lacquers and clear finishes, phase 2. 3. EU limit value for this product A/d: 130 g/l 2010. This product contains a maximum of 130 g/l VOCs. We apply the above harmonization procedure as recommended by the Dutch Green Building Council.
Belgian emission label	The product complies with the limit values and other stipulations of the Royal Decree of 8 May 2014, which defines the threshold levels for emissions to the internal environment from construction products for designated, specific uses, as published in the Belgian Government Gazette of 8 August 2014.
French emission label	A

### Item details

Packaging (l)	0.5, 1, 2.5, 5, 200
Storage	Cool and above freezing point do not allow product quality to deteriorate during storage.
Use within	12 Months in unopened packaging. After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and moulds free rein from outside, which could spoil the product.

### System composition - advices

#### **New, exterior, untreated, wood**

- clean / degrease and sand
- prime with Ralston Aqua All-Primer BIOseries
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **New, exterior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Aqua All-Primer BIOseries
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **New, exterior, untreated, plastics (hard PVC)**

- clean / degrease thoroughly, and sand
- prime with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **Existing, exterior, treated, wood**

- remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston Aqua All-Primer BIOseries
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **Existing, exterior, treated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime bare patches with Ralston Aqua All-Primer BIOseries
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **Existing, exterior, treated, plastics (hard PVC)**

- remove unsound paint coats
- clean / degrease thoroughly, and sand
- prime/ pre-finish partially or entirely with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **New, interior, untreated, wood**

- clean / degrease and sand
- prime with Ralston Aqua All-Primer BIOseries
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **New, interior, untreated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime with Ralston Aqua All-Primer BIOseries
- pre-finish with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **New, interior, untreated, plastics (hard PVC)**

- clean / degrease thoroughly, and sand
- prime with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **Existing, interior, treated, wood**

- remove unsound paint coats
- clean / degrease and sand / rub down gloss thoroughly
- prime bare patches with Ralston Aqua All-Primer BIOseries
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **Existing, interior, treated, non-ferrous metal (galvanised steel, aluminium, copper)**

- remove unsound paint coats
- remove all traces of oxidation thoroughly, clean / degrease and sand
- prime bare patches with Ralston Aqua All-Primer BIOseries
- pre-finish patches or entire surface with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

#### **Existing, interior, treated, plastics (hard PVC)**

- remove unsound paint coats
- clean / degrease thoroughly, and sand
- prime/ pre-finish partially or entirely with Ralston Aqua All-Primer BIOseries
- finish with Ralston Aqua paints

### **General remarks on paint systems and preparation**

These remarks on paint application and maintenance are only general. The appropriate paint system to be applied will depend on both the substrate and the requirements to be met by the paintwork.

### **Regularly clean and repair any damage to paintwork**

Regularly (preferably annually), clean the paintwork and repair any physical or other damage to the substrate or paintwork. This will have a beneficial effect on the condition of the painted object and its paint coating.

### **Adhesion between paint layers**

Always sand or de-gloss between paint coating layers. This is essential for good adhesion of each new layer to the previous layer (with the exception of wall paints).

### **Regularly check the dew point**

When working in lower temperatures, check the dew point frequently. Never apply new paint/coating onto a substrate with condensation (dew). If you do so, the adhesion and film formation will be degraded. Moisture also causes poor drying, and can ruin the gloss.

### **Repairs and compatibility with paint**

Repairs to substrates, paintwork, connection joints/seams and glazing systems must be carried out with the appropriate products in accordance with the manufacturer's instructions. For wood repair, we prefer wood repair products based on epoxy or polyurethane and for sealing glazing joints to the Soudal Glaskit TS. The Soudal Acryrub CF2 can be used to seal joints and seams in interior wall paintwork. Prior to the commencement of the painting work, assess the mutual tolerance of the products to be applied.

### **Pretreatment, wooden substrates**

Remove dirt and any weathered and/or degraded parts from wood and wood-based panels prior to application of the paint system in order to obtain a clean and sound substrate. By rounding off sharp edges, a longer protection of the substrate is obtained. Wood may contain up to 18% moisture during treatment.

### **For treatment, metal substrates**

Remove rust and zinc salts thoroughly, so that an oxidation-free surface is obtained. Immediately after de-rusting / sanding, degrease and apply a primer layer. Degrease new hot-dip galvanised steel and aluminium before applying a primer coat and then blast lightly with a fine non-metallic abrasive using appropriate pressure.

### **Painting of synthetic substrates**

There is no suitable paint system for synthetic materials such as PE and PP.

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Ralston Colour & Coatings B.V. expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross negligence.

# Product Data Sheet

## Ralston Aqua All-Primer BIOseries

**Ralston**  
COLOUR & COATINGS



Ralston Colour & Coatings B.V.  
Part of Royal Van Wijhe Verf  
Russenweg 14  
P.O. Box 205  
8000 AE Zwolle  
Netherlands

T : +31(0)38 - 429 11 00  
F : +31(0)38 - 421 04 14

[www.ralstoncolour.com](http://www.ralstoncolour.com)  
[info@ralstoncolour.com](mailto:info@ralstoncolour.com)

CoC 05063230