

S REDFINE+

TECHNICAL SHEETING

RED NR 35

FINE GRAIN SIZE MATERIAL HIGH WEAR SHEETING





MECHANICAL & PHYSICAL PROPERTIES

MECHANICAL

Rubber Compound	NR			
Rubber Color	Red - R397			
Density	0.95 g/cm3 ±0.05			
Hardness (ISO 48-4)	35±5 Shore A			
Tensile strength (ISO 37)	≥25 MPa			
Elongation at break (ISO 37)	≥700 %			
Tear resistance (ISO 34-1)	≥30 N/mm			
Abrasion resistance (ISO 4649)	5N ≤60mm3			
Compression set (ISO 815-1)	22h @ 70°C:≤30%			
TEMPERATURE				
Working temperature	-40/+80 °C			
AGEING				
Δ Hardness (ISO 188)	70h @ 70°C : ≤5 Shore A			
△ Tensile strength (ISO 188)	70h @ 70°C: ± 15%			
△ Elongation at break (ISO 188)	70h @ 70°C:≤-20%			

CHEMICAL RESISTANCE

Diluted acids and bases	Good
Concentrated acids and bases	Medium
Ozone	Medium
Oils and hydrocarbons	Non suitable

FEATURES

· Wear resistant natural rubber, red.

ADVANTAGES

- Excellent mechanical properties: tensile strength, elongation at break, tear resistance, abrasion, etc.
- Excellent resistance to fine grain size products projection and fretting wear: sand, shot blasting, fine particles, abrasive dust, etc.
- Great flexibility and resilience
- Corrosion protection
- Noise and vibration propagation reduction
- Possibility to be produced with bonding layer for cold vulcanizing

APPLICATIONS

- Hoppers, chutes, operating cyclones, hydrocyclones, vibrating lines, extraction pump bodies, tanks, silos, etc., linings to protect equipment against very abrasive fine grain size products wear, due to their very nature (rock, wood, metal, all fine particle size materials, chemical products, etc.), density and hardness (medium to high), forms (fine particles, bulks, etc.), with dry conditions and maximum temperature 70°C.
- Hanging panels fostering materials cleaning and removal.
- Areas of activity: sand and gravel quarries, aggregate and cement industries, concrete plants, etc.

MAINTENANCE RECOMMENDATION

 Always follow manufacturer warnings and instructions when using any cleaning product.









WEA	R SHEETII	NG		3 KEDFII	IET NO	91		KED	NK 33	
DIMENSIONS										
Article number	Stock Situation	Thickness (mm)	Width (mm)	Length (mm)	Weight	Side 1 finish	Side 2 finish	Type of insertion	Number Of Insertions	Inner car- board tube Ø mm
SSR39700003002	STD STOCK	3	1400 ±2%	10000 ±2%	2,85	Smooth	Smooth	-	0	80 mm
SSR39700004002	STD STOCK	4	1400 ±2%	10000 ±2%	3,78	Smooth	Smooth	-	0	80 mm
SKR39700005007	STD NOT STOCK	5	1500 ±2%	10000 ±2%	4,75	Bonding	Matt	-	0	80 mm
SMR39700005002	STD STOCK	5	1500 ±2%	10000 ±2%	4,75	Matt	Matt	-	0	80 mm
5011180	STD STOCK	6	1500 ±2%	10000 ±2%	5,70	Matt	Matt	-	0	80 mm
5012189	STD NOT STOCK	6	1500 ±2%	10000 ±2%	5,70	Bonding	Matt	-	0	200 mm
SKR39700008006	STD NOT STOCK	8	1500 ±2%	10000 ±2%	7,90	Bonding	Matt	-	0	200 mm
SMR39700008004	STD STOCK	8	1500 ±2%	10000 ±2%	7,56	Matt	Matt	-	0	
SKR39700010003	STD NOT STOCK	10	1500 ±2%	10000 ±2%	9,79	Bonding	Matt	-	0	200 mm
SMR39700010002	STD STOCK	10	1500 ±2%	10000 ±2%	9,45	Matt	Matt	-	0	
SKR39700012001	STD NOT STOCK	12	1500 ±2%	6000 ±2%	11,34	Bonding	Matt	-	0	200 mm
SMR39700012001	STD NOT STOCK	12	1500 ±2%	6000 ±2%	11,4	Matt	Matt	-	0	
SKR39700015002	STD NOT STOCK	15	1500 ±2%	6000 ±2%	14,25	Bonding	Matt	-	0	200 mm
SMR39700015001	STD NOT STOCK	15	1500 ±2%	6000 ±2%	14,25	Matt	Matt	-	0	
SMR39700020001	STD NOT	20	1500 ±2%	6000 ±2%	18,90	Matt	Matt	-	0	

S REDFINE+ R397

RED NR 35

0

0

200 mm

IDENTIFICATION

SKR39700025001

SMR39700025001

STOCK

STD NOT

STOCK

STD NOT

STOCK

25

25

1500 ±2%

1500 ±2%

FINE GRAIN SIZE MATERIAL HIGH

Labelling	Self-adhesive label indicating product name, dimensions, area in m^2 , nominal weight, and product code to allow product traceability. $(94/62/EC - LDPE4)$
Wrapping	Black polyethylene film. (94/62/EC - LDPE4)
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll. Bonding layer internal side protected by a white polypropylene film, easily removable by hand.

23,75

23,75

Bonding

Matt

Matt

Matt

6000 ±2%

6000 ±2%

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

