# **S GREYFINE**

### WEAR RESISTANT SHEETING

GREY NR 40

FINE GRAIN SIZE MATERIAL MEDIUM WEAR SHEETING



#### **MECHANICAL & PHYSICAL PROPERTIES**

#### MECHANICAL

Rubber Compound	NR				
Rubber Color	Grey - R488				
Density	1.05 g/cm3 ±0.05				
Hardness (ISO 48-4)	40±5 Shore A				
Tensile strength (ISO 37)	≥16 MPa				
Elongation at break (ISO 37)	≥600 %				
Abrasion resistance (ISO 4649)	5N ≤80mm3				
Compression set (ISO 815-1)	24h @ 70°C∶≤30%				
TEMPERATURE					
Working temperature	-40/+85 °C				
AGEING					
△ Hardness (ISO 188)	70h @ 70°C : ≤5 Shore A				
$\Delta$ Tensile strength (ISO 188)	70h @ 70°C : ≤ -15%				
$\Delta$ Elongation at break (ISO 188)	70h @ 70°C : ≤-20%				

#### **CHEMICAL RESISTANCE**

Diluted acids and bases	Very good		
Concentrated acids and bases	Good		
Ozone	Medium		
Oils and hydrocarbons	Non suitable		



#### **FEATURES**

• Wear resistant natural rubber, grey.

#### ADVANTAGES

- Excellent mechanical properties: tensile strength, elongation at break, tear resistance, abrasion, etc.
- Excellent resistance to fine grain size products projection and fretting wear: sand, shot blasting, fine particles, abrasive dust, etc.
- Corrosion protection
- Noise and vibration propagation reduction
- Possibility to be produced with bonding layer for cold vulcanizing or with steel backing for mechanical fixing

#### **APPLICATIONS**

- Hoppers, chutes, operating cyclones, vibrating lines, silos, etc., linings to protect equipment against very abrasive fine grain size products wear, due to their very nature (rock, wood, metal, all fine particle size materials, chemical products, etc.), density and hardness (medium to high), forms (fine particles, bulks, etc.), with dry conditions and maximum temperature +70 °C.
- Manufacturing of rubber skirts.
- Hanging panels fostering materials cleaning and removal.
- Areas of activity: sand and gravel quarries, aggregate and
- cement industries, concrete plants, etc.

#### MAINTENANCE RECOMMENDATION

• Always follow manufacturer warnings and instructions when using any cleaning product.



## FINE GRAIN SIZE MATERIAL MEDIUM WEAR SHEETING

#### **S GREYFINE R488**

#### **GREY NR 40**

#### DIMENSIONS

Article number	Stock Situation	Thickness (mm)	Width (mm)	Length (mm)	Weight	Side 1 finish	Side 2 finish	Type of insertion	Number Of Insertions	Inner car- board tube Ø mm
5013335	STD NOT STOCK	3	1400 ±2%	10000 ±2%	3,15	Smooth	Smooth	-	0	80 mm
S614880401	STD NOT STOCK	4	1400 ±2%	10000 ±2%	4,2	Smooth	Smooth	-	0	80 mm
SSR48800005001	STD NOT STOCK	5	1400 ±2%	10000 ±2%	5,25	Smooth	Smooth	-	0	80 mm
SSR48800006001	STD NOT STOCK	6	1400 ±2%	10000 ±2%	6,3	Smooth	Smooth	-	0	80 mm
SSR48800008002	STD NOT STOCK	8	1400 ±2%	10000 ±2%	8,4	Smooth	Smooth	-	0	
SSR48800010003	STD NOT STOCK	10	1400 ±2%	10000 ±2%	10,5	Smooth	Smooth	-	0	

#### **IDENTIFICATION**

Labelling	Self-adhesive label indicating product name, dimensions, area in m <sup>2</sup> , nominal weight, and product code to allow product traceability. (94/62/EC - LDPE4)
Wrapping	Black polyethylene film.(94/62/EC - LDPE4)
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

