

S REDFINE+

WEAR RESISTANT SHEETING

RED NR 35

FINE GRAIN SIZE MATERIAL HIGH WEAR SHEETING



MECHANICAL & PHYSICAL PROPERTIES

MECHANICAL

Rubber Compound	NR
Rubber Color	Red - R397
Density	0.95 g/cm ³ ±0.05
Hardness (ISO 48-4)	35±5 Shore A
Tensile strength (ISO 37)	≥25 MPa
Elongation at break (ISO 37)	≥700 %
Tear resistance (ISO 34-1)	≥30 N/mm
Abrasion resistance (ISO 4649)	5N ≤60mm ³
Compression set (ISO 815-1)	22h @ 70 °C : ≤30%

TEMPERATURE

Working temperature	-40/+80 °C
---------------------	------------

AGEING

Δ Hardness (ISO 188)	70h @ 70 °C : ≤5 Shore A
Δ Tensile strength (ISO 188)	70h @ 70 °C : ± 15%
Δ Elongation at break (ISO 188)	70h @ 70 °C : ≤20%

CHEMICAL RESISTANCE

Diluted acids and bases	Good
Concentrated acids and bases	Medium
Ozone	Medium
Oils and hydrocarbons	Non suitable

FEATURES

- Wear resistant natural rubber, red.

ADVANTAGES

- Excellent mechanical properties: tensile strength, elongation at break, tear resistance, abrasion, etc.
- Excellent resistance to fine grain size products projection and fretting wear: sand, shot blasting, fine particles, abrasive dust, etc.
- Great flexibility and resilience
- Corrosion protection
- Noise and vibration propagation reduction
- Possibility to be produced with bonding layer for cold vulcanizing

APPLICATIONS

- Hoppers, chutes, operating cyclones, hydrocyclones, vibrating lines, extraction pump bodies, tanks, silos, etc., linings to protect equipment against very abrasive fine grain size products wear, due to their very nature (rock, wood, metal, all fine particle size materials, chemical products, etc.), density and hardness (medium to high), forms (fine particles, bulks, etc.), with dry conditions and maximum temperature 70 °C.
- Hanging panels fostering materials cleaning and removal.
- Areas of activity: sand and gravel quarries, aggregate and cement industries, concrete plants, etc.
- Ricochet curtains for shooting galleries.
- Squeegee blades for scrubbing machines.

MAINTENANCE RECOMMENDATION

- Always follow manufacturer warnings and instructions when using any cleaning product.

Asbestos
FREE

Halogen
FREE

RoHS
compliant

REACH
compliant

DIMENSIONS

Article number	Stock Situation	Thickness (mm)	Width (mm)	Length (mm)	Weight	Side 1 finish	Side 2 finish	Type of insertion	Number Of Insertions	Inner car-board tube Ø mm
SSR39700003002	STD STOCK	3	1400 ±2%	10000 ±2%	2,85	Smooth	Smooth	-	0	80 mm
SSR39700004002	STD STOCK	4	1400 ±2%	10000 ±2%	3,78	Smooth	Smooth	-	0	80 mm
SKR39700005007	STD NOT STOCK	5	1500 ±2%	10000 ±2%	4,75	Bonding	Matt	-	0	80 mm
SMR39700005002	STD STOCK	5	1500 ±2%	10000 ±2%	4,75	Matt	Matt	-	0	80 mm
5011180	STD STOCK	6	1500 ±2%	10000 ±2%	5,70	Matt	Matt	-	0	80 mm
5012189	STD NOT STOCK	6	1500 ±2%	10000 ±2%	5,70	Bonding	Matt	-	0	200 mm
SKR39700008006	STD NOT STOCK	8	1500 ±2%	10000 ±2%	7,90	Bonding	Matt	-	0	200 mm
SMR39700008004	STD STOCK	8	1500 ±2%	10000 ±2%	7,56	Matt	Matt	-	0	
SKR39700010003	STD NOT STOCK	10	1500 ±2%	10000 ±2%	9,79	Bonding	Matt	-	0	200 mm
SMR39700010002	STD STOCK	10	1500 ±2%	10000 ±2%	9,45	Matt	Matt	-	0	
SKR39700012001	STD NOT STOCK	12	1500 ±2%	6000 ±2%	11,34	Bonding	Matt	-	0	200 mm
SMR39700012001	STD NOT STOCK	12	1500 ±2%	6000 ±2%	11,4	Matt	Matt	-	0	
SKR39700015002	STD NOT STOCK	15	1500 ±2%	6000 ±2%	14,25	Bonding	Matt	-	0	200 mm
SMR39700015001	STD NOT STOCK	15	1500 ±2%	6000 ±2%	14,25	Matt	Matt	-	0	
SMR39700020001	STD NOT STOCK	20	1500 ±2%	6000 ±2%	18,90	Matt	Matt	-	0	
SKR39700025001	STD NOT STOCK	25	1500 ±2%	6000 ±2%	23,75	Bonding	Matt	-	0	200 mm
SMR39700025001	STD NOT STOCK	25	1500 ±2%	6000 ±2%	23,75	Matt	Matt	-	0	

IDENTIFICATION

<i>Labelling</i>	Self-adhesive label indicating product name, dimensions, area in m ² , nominal weight, and product code to allow product traceability.
<i>Wrapping</i>	Black polyethylene film. (94/62/EC - LDPE4)
<i>Packaging</i>	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll. Bonding layer internal side protected by a white polypropylene film, easily removable by hand.

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.